MuteMat[®] Gym 51 Product Data

Description:	and easy to install Gym Fl	hly engineered, high performing oor Sound proofing platform to w frequency impact noise and		
	MuteMat [®] Gym 51 is designed for cross-fit training areas, heavy-weighted machinery and free-weights - all where higher levels of impact noise are expected.			
	Compression Moulded te with impact reducing ped	precision engineered with chnology to create a dense platform estals on the bottom to limit direct I flooring, creating a cushioning and vibration.		
Features and Benefits:	Built-in U-shaped interlocking KrosLock® de-sign. Bevelled edge, 2 mm all around.			
	Wear Layer : Made out of buffings of recycled truck tyres.			
	Bottom layer : Made out of granules of recycled truck tyres.			
Performance:	The dB reduction difference between the drop on a concrete floor and the MuteMat® Gym 51 Tile. (SPL)			
	11.11kg from 91cm	= 34.4 dB	20200	
	11.11kg from 152cm	= 30.8 dB	-00-0	(Alternative)
	24.72kg from 91cm	= 31.6 dB		
	24.72kg from 152cm	= 26.6 dB		100000000
	Impact sound reduction	ΔLw 25dB		2008 C
	Performance will vary with different floor make-up. Please see performance data for examples.			




www.iKoustic.com 01937 588226 Sales@ikoustic.com

iKoustic Limited,

Units 4 & 5, Erivan Park, Sandbeck Way, Wetherby, West Yorkshire, LS22 7DN

MuteMat[®] Gym 51 Product Data

Test Description	Results	ASTM Ref	Test Lab
Dimensions:	51mm x 610mm x 610mm	I	
Weight:	10.81 kg		
Temperature range:	-30 to 80 degrees Celsius		INT.
Hardness:	60 +/- 5 shore A		INT.
Freeze Thaw:	No deterioration	C67	SGS
Deterioration air/oven:	No deterioration	D573	SGS
Slip resistance:	Dry 102 Wet 62	E303	SGS
Slip resistance:	Dry .81 Wet .82	D2047	SGS
Anti slip property:	R10		INT.
Coefficient of friction:	> 0.3µ		INT.
Compression deflection:	29,5 PSI to 25% comp.	D1667	NWL
Compression set:	4,37% Permanent set	D395	NWL
Tensile strength:	107 PSI	D412	SGS
Tensile strength:	+/- 1 N/mm2		INT.
Elongation at break:	165%	D412	SGS
Tear strength:	6.76 kg/cm	D624	SGS
Wear Surface Density:	33kg/30dm3		
Flammability:	Class 2	E648	QAI
Burning Pill Test:	Pass	D2859	NWL







www.iKoustic.com

01937 588226 Sales@ikoustic.com **iKoustic Limited,** Units 4 & 5, Erivan Park, Sandbeck Way, Wetherby, West Yorkshire, LS22 7DN